



**READY
MIX PLASTER**

GripON Ready Mix-Plaster is a premixed cementitious based material with additive & fibers to substitute conventional site mix plaster. Due to its high content of additive it allows better shrinkage control as well as improved workability.



Packaging Size: 40 Kg Bag

Areas of Application

- GripON Ready Mix-Plaster is recommended for external & internal plastering on AAC blocks, Flyash Bricks, Ceiling, and Concrete Surface.

Features & Benefits

- Replacement to conventional plaster
- Well graded silt free sand
- Lesser curing than conventional plaster
- Lesser rebound than conventional plaster
- Fiber for crack resistance & durability
- Minimal wastage

Application Methodology

Surface Preparation

- The surface should be sound and thoroughly clean to remove all oil, grease and dirt. Surface should be in level to achieve desired coverage. Wet the surface before application of plaster to prevent premature loss of water.

Mixing

- Mix manually or mechanically a 40kg bag of GripON Ready Mix-Plaster with 6 to 7 lit of clean water until a homogeneous paste is obtained. Let the mix rest for a few minutes.

Method of Application

- Apply the mixed GripON Ready Mix-Plaster by hand using a steel trowel at a thickness between 10-12 mm in one layer. Finish the surface with wooden or steel float as required. Let the GripON Ready Mix-Plaster set properly on the surface before any curing. If more thickness is required, the application should be done in two layers. The 1st layer should be roughened then cured. The 2nd layer should be applied after curing of at least 48 hrs. Maximum thickness of plaster should not exceed 20-22 mm.

Technical Information

Appearance	Cement Grey Powder
Grain Size	Upto 2.5mm
Mixing Ratio	6 to 7 lit per 40 kg bag
Shelf Life	6 months pack sealed and stored in Dry conditions
Compressive strength	≥ 6 Mpa @ 28 days
Pull off Adhesion	≥ 0.3 Mpa
Coverage	10-12 Sq.ft./ 40kg Bag @ 20-22mm Thickness
	16-18 Sq.ft./ 40kg Bag @ 10-12mm Thickness

Packaging - Available in 40kg bag

Health & Safety

- GripON Ready Mix-Plaster is non - hazardous. It should not be swallowed or allowed to come in contact with skin or eyes. Suitable protective goggles & gloves should be worn. In the case of contact with eyes, rinse immediately with plenty of water & seek medical advice. If swallowed, seek medical attention immediately, do not induce vomiting.